



**BANGTAI TPU**

Baoding Bangtai Polymeric New-materials Co.,Ltd

**HIND ELASTOMERS PVT LTD**  
702/703 Prasad Chambers  
Tata Road No.2, Swadeshi Mills Compound  
Opera House, Mumbai - 400 004  
Tel: 022 - 23612222 / 23632222  
Email: mail@hindelastomers.com  
GST: 27AAACH1153J1ZS

## Thermoplastic polyurethane-TPU

# 6126HH

Technical data

## Solvent-based TPU

### ■ Features

With high crystallization rate and especially has great bonding capacity with TPU, PVC, NYLON,and fabric. Excellent initial bonding strength, good solvent solubility ,quick crystallization

### ■ Application

SHOE adhesive

### ■ Properties

Properties	Unit	Value
Viscosity	cps	3600-4200
Solid content	%	15
Activation Temp	°C	55-75
Crystallization rate	---	fast
Tack time	PVC vs PVC( mins )	6-12
Initial bonding strength	PVC vs PVC after 5 mins (kg/3cm)	10-16

Pls note:

1, 15% solution in MEK using high speed stirrer,solid content of solution to be checked to adjust to the volume) on NDJ-1,SPL-3,RPM-12 at 25°C.

2, Data listed above are just for reference, the detailed data are subjected to practical production.

3, Other grades available, please consult me for further material requirements.

Package: Normally 25kg/bag

### ■ Certification



### ■ Environmental&Health& Safty

Take MSDS for reference.

### ■ Shelflife and Storage

A minimum storage time of one year since the date of production can be expected if stored cool (10-25°C), dry and protected from direct sun light in well closed original packaging.