



HiFlex™ EP-201 is a blended terpolymer of ethylene, propylene and diene. **HiFlex™ EP-201** has very good processability and is compatible for co-curing with conventional diene rubbers. It shows excellent resistance to oxidation and ozone degradation.

RAW MATERIAL PROPERTIES

Properties	Nominal Value	Test Method
Mooney Viscosity (ML 1+4@125°C)	60 +/- 10 MU	ASTM D1646
Ethylene Content	63 +/- 5%	Internal Method
ENB Content	5 +/- 1%	Internal Method
Moisture Content	1.0% max	Internal Method
Ash Content	1.5% max	ASTM D297-35
Density	0.86 g/cm ³	ISO 1183
Antioxidant	Non-Staining	-

Physical Properties*	Value
Tensile Strength	14.2 MPa
Modulus at 100% EB	4.3 Mpa
Elongation at Break	400%
Hardness	65 Shore A

* Characteristics determined on a HEPL compound of the following formulation. Press Cure: 10 mins @ 160°C

HiFlex™ EP-201	100
Zinc Oxide	5
Stearic Acid	1
FEF N-550	80
Paraffinic Oil	20
Qureacc® TMT	0.5
Qureacc® MBT	0.5
Qureacc® ZDBC	1
Qureacc® MBTS	1
Sulfur	1.7

Applications:

Automotive and window profiles, grommets, pipe seals, sheets, and other industrial products requiring ozone resistance.

Supply Form:

34 kgs bale wrapped in dispersible film.